

TOPCRET

BAXA8

Installation guide

The Experts Choice

01

MICROCEMENT - Base Layers



Components:

BASE POWDER + BASE LIQUID (GREEN)

Mixing ratio:

2 (or 3) parts of powder : 1 part of liquid

1st step: mix the components (with a helix mixer)

2nd step: Install “2” layers of the mixed material (Metal trowel)

Sanding: 150grit (between each layer)

Drying time: 2 hours each layer

*Mix has to be of a creamy consistency, if it results too liquid, add half part more of powder. If too dense, half part more of liquid.

02

BAXAB - Base Layer



Components:

LIQUID A + LIQUID B + COMPONENT C (COLOR POWDER)

Mixing ratio:

1 part(liquid A) : 2 parts(liquid B) : 3 parts(comp C)

1st step: Mix A + B, then add C (mix with a helix mixer)


2nd step: Install "1" layers of the mixed material (Metal trowel)

Sanding: 150grit (between each layer)

Drying time: 6 hours

03

BAXAB NF - Smooth finish layers + Protection



Components:

NF POWDER + NF LIQUID + NF HARDENER

Mixing ratio:


150g(NF Powder) : 100g(NF Liquid) : 16g(NF Hardener)

1st step: First mix NF POWDER + NF LIQUID, then add NF HARDENER(mix with a helix mixer)

2nd step: Install "2" layers of the mixed material (Metal trowel or plastic trowel)

Sanding: 150grit(between each layer)

Drying time: 2 hours



Components:

CRED COMPONENT 1 + CRED COMPONENT 2

Mixing ratio:

87 %(Component 1) : 13 %(Component 2)

1st step: mix the components(with a helix mixer)

2nd step: Install "2" layers of the mixed material(Plastic trowel only)

Drying time: 2 hours

TOOLS AND MATERIAL NEEDED



MDF/WOOD PLAQUE
(50X50 CM OR MAX. 100X100 CM)



METAL TROWEL (FOR BASE)



PLASTIC TROWEL (FOR BAXAB,
AND FOR “LESS MARKED” FINISH)




SANDING PAPER (150 GR)



DRILL + HELIX MIXER
(FOR MIXING OF COMPONENTS)



A SCALE



CLEAN BUCKETS

The Experts Choice

london@topcret.com
Phone: +44 (0) 20 7624 2180

Office & Showroom:
4 Hampstead West
224 Iverson Rd, London NW6 2HL
LONDON - UK

info@topcret.com
T. +34 932 74 12 08

Oficina Central TOPCRET:
Gran Via de les Corts Catalanes,
828, 08013 BARCELONA
ESPAÑA

TOPCRET



WWW.TOPCRET.COM



Management
System
ISO 45001:2018
ISO 14001:2015
ISO 9001:2015
www.tuv.com
ID: 9108638925

