

TOPCRET

MICROCEMENTO®

**Installation
guide**

The Experts Choice

01

TOPCRET BASE - Base Layers



Components:

Topcret® Base Powder [A] - Topcret® Base Liquid [B] (green)

Mixing ratio:

2 to 3 parts [A] : 1 part [B]

1st step: mix the components (with a helix mixer)

2nd step: Install “2” layers of the mixed material (Metal trowel)

Sanding: 150grit (between each layer)

Drying time: 2 hours each layer

*Mix has to be of a creamy consistency, if it results too liquid, add half part more of powder. If too dense, half part more of liquid.

02

MICROCEMENT - Finish Layers



Components:

Microcemento® Powder [A] - Microcemento® Concentrated Liquid [B] (white)

Mixing ratio:

2 parts [A] : 1 part [B]

1st step: mix the components (with a helix mixer)

2nd step: Install “2” layers of the mixed material (Metal trowel)

Sanding: 150grit (between each layer)

Drying time: 2 hours each layer

03

MICROCEMENT - Protection Layers



Components:

WATERPROOF, SEALANT, AND WAX

1st step: 1 Waterproof - 1 layer

2nd step: 2 Sealant - 2 layers

3rd step: 3 Wax - 2 layers

Drying time: 1 hours each layer

***Important:** Use sponge trowel to apply

TOOLS AND MATERIAL NEEDED



**MDF/WOOD PLAQUE
(50X50 CM OR MAX. 100X100 CM)**



METAL TROWEL (FOR BASE AND ECOCEMENTO)



SANDING PAPER (150 GR)




**DRILL + HELIX MIXER
(FOR MIXING OF COMPONENTS)**



SPONGE TROWEL (ECOCEMENTO PROTECTION SYSTEM)



A SCALE



CLEAN BUCKETS + SMALL PLASTIC GLASS

The Experts Choice

london@topcret.com
Phone: +44 (0) 20 7624 2180

Office & Showroom:
4 Hampstead West
224 Iverson Rd, London NW6 2HL
LONDON - UK

info@topcret.com
T. +34 932 74 12 08

Oficina Central TOPCRET:
Gran Via de les Corts Catalanes,
828, 08013 BARCELONA
ESPAÑA

TOPCRET



WWW.TOPCRET.COM



Management
System
ISO 45001:2018
ISO 14001:2015
ISO 9001:2015
www.tuv.com
ID: 9108638925

