

SYSTEM

BAXAB SMOOTH

APPLICATION

WALLS, INTERIOR AND EXTERIOR FLOORS

✓	LAYERS	DRYING HOURS	RECOMMENDED TROWEL	SANDPAPER TYPE	CONSUMPTION
01	TOPCRET BASE + FIBER MESH	2 HOURS	METALLIC	150G	(2 LAYERS) BASE POWDER = 1.8 KG/M2 BASE LIQUID = 0.67 L/M2
02	TOPCRET BASE	2 HOURS	METALLIC	150G	
03	BAXAB® BASE (ex Baxab)	6 HOURS	METALLIC	150G	(1 LAYER) BAXAB LIQUID (A) = 0.1 L/M2 BAXAB LIQUID (B) = 0.2 L/M2 BAXAB POWDER (C) = 0.4 KG/M2
04	BAXAB® FINISH (ex Baxab NF)	2 HOURS	METALLIC/FLEXIBLE/PLASTIC	150G	(2 LAYERS) NF POWDER = 0.30KG/M2 NF LIQUID = 0.20L/M2 NF HARDENER = 0.032 L/M2
05	BAXAB® FINISH (ex Baxab NF)	2 HOURS	METALLIC/FLEXIBLE/PLASTIC	150G	
06	CRED® ARMOR	2 HOURS	PLASTIC		(2 LAYERS) COMPONENT 1 = 0.087L/M2 COMPONENT 2 = 0.013L/M2
07	CRED® ARMOR	2 HOURS	PLASTIC		

	TOTAL LAYERS	7
	TOTAL DRYING TIME BETWEEN COATS	18 HOURS
	24 HOURS: LIGHT PEDESTRIAN TRAFFIC ALLOWED	
	YOU CAN NOW COVER YOUR FLOOR WITH A BREATHABLE MATERIAL (WE RECOMMEND MDF PANELS). REMOVE IT OVERNIGHT SO THE FLOOR CONTINUES TO HEAL.	
	5 DAYS: NOW YOU CAN REPOSITION YOUR FURNITURE OR UNITS WITH NEW, CLEAN THE FELT PADS TO AVOID UNNECESSARY DAMAGE.	
	7 DAYS: AVOID ACCUMULATION OF WATER AND IN CASE OF CONTACT WITH WATER, DRY IT AS SOON AS POSSIBLE.	
	TYPE OF COLORING	POWDER