

SYSTEM

MICROCEMENT SMOOTH

APPLICATION

WALLS, INTERIOR AND EXTERIOR FLOORS

✓	LAYERS	DRYING HOURS	RECOMMENDED TROWEL	SANDPAPER TYPE	CONSUMPTION
01	TOPCRET BASE + FIBER MESH	2 HOURS	METALLIC	150G	(2 LAYERS) POWDER = 1.8 KG/M2 LIQUID = 0.67 L/M2
02	TOPCRET BASE	2 HOURS	METALLIC	150G	
03	MICROCEMENTO® SMOOTH	2 HOURS	METALLIC/FLEXIBLE	150G	(2 LAYERS) POWDER = 0.8 KG/M2 LIQUID = 0.4 L/M2
04	MICROCEMENTO® SMOOTH	2 HOURS	METALLIC/FLEXIBLE	150G	
05	WATERPROOFING	1 HOUR	SPRAYER + SPONGE		(1 LAYER) LIQUID = 0.06 L/M2
06	SEALANT	1 HOUR	SPONGE		(2 LAYERS) LIQUID = 0.03 L/M2
07	SEALANT	1 HOUR	SPONGE		
08	WAX	1 HOUR	SPONGE		(2 LAYERS) LIQUID = 0.03 L/M2
09	WAX	1 HOUR	SPONGE	SAND IF GOES MORE THAN ONE HOUR	

	TOTAL LAYERS	9
	TOTAL DRYING TIME BETWEEN COATS	13 HOURS
	24 HOURS: LIGHT PEDESTRIAN TRAFFIC ALLOWED	
	YOU CAN NOW COVER YOUR FLOOR WITH A BREATHABLE MATERIAL (WE RECOMMEND MDF PANELS), REMOVE IT OVERNIGHT SO THE FLOOR CONTINUES TO HEAL.	
	5 DAYS: NOW YOU CAN REPOSITION YOUR FURNITURE OR UNITS WITH NEW, CLEAN THE FELT PADS TO AVOID UNNECESSARY DAMAGE.	
	7 DAYS: AVOID ACCUMULATION OF WATER AND IN CASE OF CONTACT WITH WATER, DRY IT AS SOON AS POSSIBLE.	
	TYPE OF COLORING	POWDER